

DECORATIVE

DECORK

Cork based decorative finish applicable on walls, floors and facades.

Decorative finish made of cork and water based resins (grain size 0 – 1 mm; 0 – 0.04 in) for the decoration of floors, walls, ceilings and facades, for indoor and outdoor. The coating has all the benefits of cork: breathability, thermal insulation, an excellent fire reaction, weathering resistance and durability. It is possible to create endless aesthetical effects, which can have different textures.

BENEFITS

- Suitable to create decorative effects.
- Suitable for indoor and outdoor.
- Breathable and water-repellent.
- Elastic.
- Excellent aesthetic effect.
- Easy and quick application.
- LEED accredited and CE branded.

YIELD

0.8 – 1.0 kg/m² in 2 coats.

0.16 – 0.2 lb/ft² in 2 coats.

COLOR

Diasen color chart.

APPLICATION FIELDS

Product designed for the coating and the decoration of internal walls, ceilings, floors and external facades. *Decork* shows excellent adhesion abilities on any kind of support and for this reason, with the correct primer, it can be used on different substrates: metal, plaster, cement supports and tiles. *Decork* is suitable both indoor and outdoor.

PACKAGING

18 kg (39.6 lb) plastic bucket + 2 kg (4.4 lb) of color.
Pallet: 32 bucket (576 kg – 1267.2 lb) + 32 packaging of color (64 kg – 140.8 lb).

UB1 Color

18 kg (39.6 lb) plastic bucket + 4.5 kg (9.9 lb) of color.
Pallet: 32 bucket (576 kg – 1267.2 lb) + 32 packaging of color (144 kg – 316.8 lb).

STORAGE

Store the product in its original containers perfectly closed, in well ventilated areas, away from sunlight, water and frost, at temperatures between +5°C and +35°C (41°F and 95°F).
Storage time: 12 months.

PREPARATION OF SUPPORT

The support must be completely hardened and resistant enough. The surface must be perfectly levelled, thoroughly clean, dry, well consolidated, without oils, greases debris or detaching parts or other materials that may compromise the product adhesion.

If the surface is crumbly in its entirety, totally scrape it until obtaining a good support and restore lesions or damaged parts with suitable mortar.



Diasen srl
Zona Industriale Berbentina, 5 Sassoferrato ANCONA
14
EN 1504-2
Products and systems for the protection and the
restoration of concrete structures–
Part 2: Protection systems of concrete surface

Thermal conductivity:
Water vapour permeability:

$\lambda = 0.086 \text{ W/mK}$
 $\mu = 15$



For application videos,
product page, safety data
sheet and other information.

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on www.diasen.com.

DECORK

Cork based decorative finish applicable on walls, floors and facades.

| Technical Data | | |
|---|---|--|
| Features | | Unit |
| Yield | 0.8 – 1.0 in two coats 0.16 – 0.2 in two coats | kg/m ² lb/ft ² |
| Aspect | paste | - |
| Colour | Diasen color chart | - |
| Dilution | By trowel | If necessary max 5% (0.9 l – 0.2 gal per 18 kg – 39.6 lb bag) |
| | By spray | If necessary max 10% (1.8 l – 0.47 gal per 18 kg – 39.6 lb bag) |
| Waiting time between 1 st and 2 nd coat (T=23°C/73.4°F; R.H. 50%) | about 8 - 10 | hours |
| Grain size | 0 – 1 0 – 0.04 | mm in |
| Application temperature | +5 /+35 +41/+95 | °C °F |
| Drying time (T=23°C/73.4°F; R.H. 50%) | 10 | hours |
| Storage | 12 months in original containers and well ventilated areas 18 kg (39.6 lb) plastic bucket + 2 kg (4.4 lb) of color | months |
| Packaging | UB1 Color: 18 kg (39.6 lb) plastic bucket + 4.5 kg (9.9 lb) of color. | kg |

| LEED® Credits | | |
|-----------------------|---|--------------|
| Standard GBC HOME | | |
| Thematic area | Credit | Points |
| Energy & Atmosphere | EAp1 - Minimum Energy Performance | mandatory |
| | EAp2 – Minimum Performance of matt package | mandatory |
| | EAc1 - Optimize Energy Performance | From 1 to 27 |
| | EAc2 – Advanced performance of matt package | 2 |
| Materials & Resources | MRp2 – Construction Waste Management | mandatory |
| | MRC2 - Construction Waste Management | From 1 to 2 |
| | MRC3 – Low Emitting Materials | From 1 to 3 |
| | MRC4 – Recycled Content | From 1 to 2 |
| | MRC5 – Regional Materials | From 1 to 2 |
| | MRC6 – Rapidly Renewable Materials | 2 |

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on www.diasen.com.

DECORK

Cork based decorative finish applicable on walls, floors and facades.

Standard LEED for New Construction & Major Renovation, LEED for Schools, LEED for Core & Shell, v. 2009

| Thematic area | Credit | Points |
|------------------------------|--|--------------|
| Energy & Atmosphere | EAp2 - Minimum Energy Performance | Mandatory |
| | EAc1 – Optimize Energy Performance | From 1 to 19 |
| Materials & Resources | MRC2- Construction Waste Management | From 1 to 2 |
| | MRC4 – Recycled Content | From 1 to 2 |
| | MRC5 – Regional Materials | From 1 to 2 |
| | MRC6 - Rapidly Renewable Materials | 1 |
| Indoor Environmental Quality | IEQc3.2 - Construction Indoor Air Quality Management Plan—Before Occupancy | 1 |
| | IEQc4.2 - Low Emitting Materials - Paints and Coatings | 1 |

| Final performances | | Unit | Regulation | Results |
|--|--------------------------|-----------------|--------------|---------|
| Elasticity | 60% | - | ISO 527-1 | - |
| Crack Bridging Ability | 2.5 0.099 | Mm in | - | - |
| Weathering Test | 1680 hours (10 year*) | hours/ years | EN ISO 11507 | - |
| Thermal conductivity (λ) | 0.086 | W/mK | EN 12667 | - |
| Water vapour permeability | $\mu = 15$ | - | EN ISO 7783 | - |
| Abrasion resistance of the system <i>Decork + Aquafloor Eco</i> (shiny version) Taber Wear Index | 70 | - | ASTM D 4060 | - |
| Abrasion resistance of the system <i>Decork + Aquafloor Eco</i> (matt version) Taber Wear Index | 55 | - | ASTM D 4060 | - |

* 1680 hours of weathering test are equal to about 10 years. This equivalence is merely indicative and it may vary depending on the weather conditions of the place where the product will be used.

The above data, even if carried out according to regulated tests are indicative and they may change when specific building site conditions vary.

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on www.diasen.com.

DECORK

Cork based decorative finish applicable on walls, floors and facades.

In case of hydro-cleaning, wait for the complete drying of the support.

Potential humidity in the support or the vapour due to radiation may compromise the adhesion of the applied product.

On horizontal flat surfaces consider suitable scope to allow the water down flow.

Decork adheres to different kind of support without the primer, it is anyway recommended to perform a test to verify the adhesion or the need to use a primer.

Diathonite plasters or new plasters

Make sure that the plaster is well levelled so it is as smooth as possible. Otherwise, apply a layer of a suitable Diasen's smoother (see technical data sheet). Both on plaster and directly on plaster apply the specific fixative *D20* (see technical data sheet).

In case of weak surface and with micro cracks, apply the white foundation *Color Primer* (see technical data sheet).

Old plaster

Make sure that the plaster is compact and well bonded to the support, otherwise partially or totally remove it and re-make it.

In case of painted plasters, according to the wide range of paints on the market, it is recommended to perform an adhesion test to verify the suitability for the application or the need to use the primer *D20* and/or *Color Primer* (see technical data sheet).

On rough plasters, *Decork*, can directly be applied. In case of dusty supports, use the fixative *D20* (see technical data sheet).

Plasterboard

On plasterboard surfaces, make sure that the joints are sealed and smoothed. Apply the fixative *D20* (see technical data sheet).

Concrete

In case of new realised cement substrate, this must be sufficiently cured.

In presence of lesions, holes or irregular areas, restore them with suitable cement mortar.

For a better adhesion on smooth and not moist concrete, it is recommended to smooth it, clean it and then apply *Grip Primer* (see technical data sheet).

For the treatment of iron bars, apply the *Anticorrosive 2K* (see technical data sheet).

To obtain a better adhesion on smooth and not absorbent concrete, it is recommended the use of *Grip Primer* (see technical data sheet).

On moist supports, in order to avoid blistering or detachment phenomena, use *Vapostop* (see technical data sheet).

If the support is affected by rising damp, it is necessary the use of *WATstop* (see technical data sheet). *WATstop* can also be used to fill small cracks and to level the support.

On rough concrete use the primer *Vapostop*.

Tiled floors

Make sure that the tiles are well bonded to the support, otherwise remove them and restore them with suitable cement mortar.

The tiled surface must not present traces of detaching substances as greases, oils, chemical products etc.

Carefully clean the support and treat the surface with *Grip Primer* (see technical data sheet).

To fill tiles joints and to create a perfectly levelled surface, use *Vaposhield* (see technical data sheet) applied by hand with steel or rubberized trowel in two coats. *Vaposhield* must be used even if the support is moist or affected by rising damp.

According to the wide range of tiles on the market, it is recommended to perform a test to verify the correct adhesion of the system.

Wood

Thoroughly clean the surface by removing dust, debris and detaching parts. The wood must be completely dry, well resistant and stable.

Treat the wooden surfaces with the primer *Grip Primer* (see technical data sheet) before the application of *Decork*.

Do not apply the product on wooden supports, matchboarding or on supports with many joints.

Metal

Thoroughly clean the surface by removing all dirt and potential varnishes not well attached.

Before the application of *Decork*, apply *Grip Primer* (see technical data sheet) on the surface.

In presence of rust, before the application of *Grip Primer*, treat the surface with *Rust Converter* (see technical data sheet).

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on www.diasen.com.

DECORK

Cork based decorative finish applicable on walls, floors and facades.

If the metal surface is painted, it is recommended to perform a test to verify the correct adhesion of the system.

Smooth surfaces

On particularly smooth and not absorbent surfaces use the specific primer *Grip Primer* (see technical data sheet).

For supports not mentioned in technical data sheet, please contact Diasen technical department.

Treatment of joints

Potential joints on the supports (joints between panels made of concrete or of other materials, expansion, control or insulation joints) must be treated, before the application of *Decork*, with the polyurethane sealant *Diaseal Strong* (see technical data sheet).

Treat points in contact with doorsteps or windows with the sealant *Diaseal Strong*.

MIXING

Always mix the product before the application with helical drill until obtaining a homogeneous mixture.

- Completely pour the content of the bag in the bucket and add the entire colour.
- Mix the compound for at least 2 or 3 minutes, until obtaining a mixture with uniform colour.
- The product is ready to use and generally it does not need to be diluted. In extremely hot climatic conditions, it is possible to add:
 - For **hand application**, maximum 5% of water (0.9 l - 0.2 gal of water each 18 kg – 39.6 lb packaging).
 - For hopper **gun application**, maximum 10% of water (1.8 l – 0.47 gal per 18 kg – 39.6 lb packaging).
- It is recommended to dilute the product always in the same way to avoid colour changes.
- Mix again the compound.

Never add other substances to the product.

APPLICATION

Application by hand

1. Wait for the complete drying of the primer possibly used.
2. Apply a first abundant coat of *Decork* by steel trowel with rounded edges. The first layer can be used as a smoothing layer to uniform the surface. In case of rain over not completely dry product, carefully verify the suitability of the next covering.
3. When the first layer is completely dry (about 10 hours at 23°C/73.4°F and 50% relative humidity), apply a second thin of product to finish. Do not use too much product for the second coat. For a better result and a more homogeneous coating, it is recommended to cross the coats.
4. Smooth as soon after the application with a 45° rounded edge plastic trowel
5. Application time: about 80/110 m² – 860.8/1183.6 ft² per day.

Application with hopper gun DS-Spray Gun

1. Wait for the complete drying of the primer possibly used.
2. The hopper gun must have:
 - minimum pressure of the compressor 5.0 bar;
 - nozzle diameter 8.0 mm – 0.31 in.
3. Apply a first coat of *Decork* to cover the whole surface. In case of rain over not perfectly dry product, carefully verify the suitability of the next covering.
3. When the first coat is completely dry (about 10 hours at 23°C/73.4°F and 50% relative humidity), apply a second coat of *Decork* until complete covering of the substrate. To obtain a better result and a more homogeneous coating, it is recommended to cross the coats.
4. Do not smooth.
5. Application time: about 200/250 m² - 2152/2690 ft² per day.

Decork can also be applied by **spraying machine** DS-5500 Texture Sprayer, nozzle diameter 4.00 mm – 0.16 in, pressure level 4 (4.0 atm); in this case, the application time ranges from 700 and 800 m² – 7532 and 8608 ft² per day.

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on www.diasen.com.

DECORK

Cork based decorative finish applicable on walls, floors and facades.

At the end of the application of the second coat, to obtain a smooth surface, the finish *Decork* can be sanded and then protected with *Aquaflor Eco* (see technical data sheet).

For floor applications, the decorative finish *Decork* must always be protected with *Aquaflor Eco* (see technical data sheet).

To create decorative effects, the finish *Decork* must be applied in combination with *Decorkoat* (see technical data sheet) and must be sanded. Then protect the surface with *Aquaflor Eco* (see technical data sheet).

DRYING TIME

At a temperature of 23°C/ 73.4°F and 50% relative humidity, the product dries in about 10 hours.

- Drying time is influenced by environmental relative humidity and by temperature and may significantly change.
- Protect *Decork* during the drying from rain, frost, direct sunlight and wind for at least 2 hours at a temperature of 23°C/73.4°F.
- If applied in higher amount than the expected ones, drying time may significantly increase.

SUGGESTIONS

- Do not apply at environmental temperature or at support temperature lower than +5°C (41°F) and higher than +35°C (95°F).
- During summer season apply the product in the cooler hours of the day, away from sunlight.
- Do not apply with imminent threat or frost, in conditions of strong fog or with relative humidity level higher than 70%.
- Apply the product on completely dry surfaces.
- Protect the product from pouring rain until complete drying.
- Before the product application, it is recommended to cover each element that will not be coated.
- Store the unused product in the original packaging.

CLEANING

Wash tools with water right after the use.

When the product is completely dry, for the cleaning, it is recommended to use neutral and not aggressive detergents. Choose the most suitable cleaning method (sponge, brush or high-pressure water jet machine) according to the type of dirt.

SAFETY

While handling, always use personal protective equipments and respect the instructions described in product safety data sheet.



Ecological Building Systems

For stockist information and full technical support for your project, please contact Ecological Building Systems or visit www.EcologicalBuildingSystems.com

