

Technical Data Sheet



Thermal	
Thermal Conductivity	0.039 Wm ⁻¹ K ⁻¹
Density	18 kg/m ³
Specific Heat Capacity	1800 Jkg ⁻¹ K ⁻¹
Vapour Resistivity	9 MNsg-1m ⁻¹

Material Protection	
Mould Resistance CUAP 2002-01-25	Pass
Moth/Beetle Proofing ISO 3998	Pass

Fire	
BS 5803-4, Flammability & Smoulder Resistance	Pass
EN11925-2, Reaction to Fire	Pass
Fire Classification	EuroClass E

Physical	
Recoverability and thickness, EN 823	Pass
Dimensional stability to EN 1604	Pass

Hygrothermal					
Porosity			45.8%		
'Surface' water absorption coefficient (kg/m ² . h ^{0.5})			0.99 (18%)		
'Edge' water absorption coefficient (kg/m ² . h ^{0.5})			0.64 (8.8%)		
Water Vapour Resistance Factor, μ			(-) Dry:1.27 (4.9%) (-) Wet:0.80 (11.8%)		
Vapour sorption:					
Relative Humidity					
Sorption	0%w/w	30%w/w	50%w/w	75%w/w	95%w/w
Moisture Content	0.00%	4.56%	7.21%	10.07%	14.84%
Deviation		(3.3%)	(7.3%)	(7.3%)	(1.9%)
Relative Humidity					
Desorption	95%w/w	75%w/w	50%w/w	30%w/w	0%w/w
Moisture Content	14.84%	11.42%	8.62%	6.09%	0.00%

Eden Renewable Innovations Ltd

Sales & General Enquiries: 017684 86285 | enquiries@thermafleece.

www.thermafleece.com



Technical Data Sheet



Environmental	
GWP (A1-A3) total	0.05 kgCO _{2e} R1 Functional Unit
GWP (A1-C4) total	0.95 kgCO _{2e} R1 Functional Unit
GWP (A1-D) total	-0.31 kgCO _{2e} R1 Functional Unit
Recycled Content	20%
Recyclable	Yes
EPD registration no	S-P-04468
EPD valid to	31/10/26
Manufactured to ISO 14001	Certificate No: 23/3478

Acoustic							
Sound absorption			NRC 1.05 @ 100mm				
Sound reduction			Rw 40dB @ 75mm				
Can be used to achieve airborne sound reduction of R _w			41dB				
Freq HZ		125	250	500	1000	2000	4000
Cosywool 50mm	Absorption Coefficient	0.2	0.4	0.65	0.75	0.85	0.95
Cosywool 75mm		0.25	0.6	0.85	0.9	0.95	1
Cosywool 100mm		0.45	0.85	1	1	1	1
Cosywool 140mm		0.6	0.9	0.95	1	1	1

Air Quality	
TVOC	9 µg/m ³ @ 3 days, n.d. @ 28 days
Carcinogenic compounds	n.d. @ 3days, n.d. @ 28days
Formaldehyde	<2 µg/m ³ @ 3 days, <2 µg/m ³ @ 28 days

Quality	
Manufactured to ISO 9001	Certificate No: 23/3477
Dimensional stability to EN 1604	Pass

Dimensions	
Thicknesses (+20mm/-0mm)	25, 50, 75, 100, 140, 150 mm
Widths (+20mm/-10mm)	370 & 570 mm
Roll Lengths (+5%/-0%)	12.0 (25mm)13.0 m (50mm), 8.5 m(75mm), 6.5 m (100 mm), 4.6 m (140mm), 4.3 m (150mm)

Eden Renewable Innovations Ltd

Sales & General Enquiries: 017684 86285 | enquiries@thermafleece.com

www.thermafleece.com



For over 20 years, Ecological Building Systems has been at the forefront of environmental and sustainable building products supplying a range of innovative airtightness solutions and natural insulations backed up with expert technical support.

As product suppliers in the UK and Ireland, we're happy to assist you with your projects and have expert technical and sales advice on hand.



Call us

Great Britain +44 (0)1228 711511

Ireland +353 46 9432104



Email us

info@ecologicalbuildingsystems.com



Find us

Great Britain Ecological Building Systems UK Ltd.,
Cardewlees, Carlisle, Cumbria, CA5 6LF,
United Kingdom

Ireland Ecological Building Systems Ltd.,
Main Street, Athboy. Co. Meath, C15 Y678,
Republic of Ireland