



### Technical data

		Material
Protective and covering fleece		Polypropylene
Functional film		Polypropylene

  

Property	Regulation	Value
Colour		Green
Surface weight	BS EN 1849-2	130 g/m <sup>2</sup>
Thickness	BS EN 1849-2	0.45 mm
Water vapour resistance factor $\mu$	BS EN 1931	5 000
sd value	BS EN 1931	2.30 m
g value	BS EN 1931	11.5 MN-s/g
Reaction to fire classification	BS EN 13501-1	E
Outdoor exposure		3 months
Outdoor exposure on retrofits betw. 2 insulation layers		14 days ; 7 days at $\leq 10$ °C
Watertight joints with 'connect' adhesive strips or TESCON tape	BS EN 13859-1	W1
Watertightness to liquid water	BS EN 1928	W1
Water column	BS EN ISO 811	> 2 500 mm
Airtightness	BS EN 12114	Tested
Tensile strength MD/CD	BS EN 12311-2	230 N/5 cm / 200 N/5 cm
Elongation MD/CD	BS EN 12311-2	90% / 90%
Nail tear-resistance MD/CD	BS EN 12310-1	120 N / 115 N
Durability after artificial ageing	BS EN 1296 / BS EN 1931	Passed
Temperature resistance	EN 1109, EN 1296, EN 1297	Permanent -40 °C to 100 °C ; -40 °F to 212 °F
Thermal conductivity		0.04 W/(m-K)
CE labelling	BS EN 13984	Yes

### Areas of application

For use as a vapour control (alternate terms: vapour check or retarder) membrane and airtight membrane directly on top of sheathing underneath suitable external roof insulation made of all insulation materials on structures that are open to diffusion on the exterior (roofing underlay with SOLITEX MENTO 3000, for example).

In addition, DA can be installed as an airtight and vapour control membrane between two layers of insulation on roof retrofit projects. All fibrous insulation materials can be used for insulation installed between rafters; the external roof insulation must be a foam insulation material (e.g. consisting of PUR, PIR or EPS). Please contact Technical Support at pro clima in Germany for assistance with calculating the thickness of the external foam insulation that is required from a building physics viewpoint. If necessary, the outer sealing layer should be implemented using a diffusion-open roofing underlay membrane (e.g. SOLITEX MENTO 3000).

### Supply form

Art. no.	Length	Width	Contents	Weight	Sales unit	Container	GTIN
10098	50 m	1.5 m	75 m <sup>2</sup>	10 kg	1	20	4026639011947

### Advantages

- ✓ Protects building structures against weathering during the construction phase for roof pitches of 10° and higher
- ✓ Water-resistant and waterproof, can be walked on
- ✓ Acts as a vapour control and airtightness layer simultaneously
- ✓ Excellent values in hazardous substance testing, has been tested according to the ISO 16000 evaluation scheme

### General conditions

pro clima DA is to be installed with the printed side facing the installation technician. The membrane is to be installed horizontally (parallel to the eave) in a taut manner. The weight of the insulation material must be supported by the sheathing.

Airtight seals can only be achieved on vapour control (alternate terms: vapour check or retarder) membranes that have been fitted with no folds or creases. Ventilate regularly and systematically to prevent the build-up of excessive humidity (e.g. during the construction phase). Occasional, intermittent ventilation is not sufficient to remove large quantities of moisture due to construction work from a building; use a dryer if necessary.

To avoid condensation formation, the thermal insulation should be installed immediately after the airtight installation of DA. This applies particularly to work carried out in winter.

#### Fastening

- Overlap the membranes by at least 10 cm.
- Use fastening staples that are at least 10 mm wide by 8 mm long to attach the membranes. The membranes can only be fastened in a protected manner in the overlap area. The maximum distance between fasteners is 10 to 15 cm.



Tested for hazardous substances according to



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about application and construction is given in the pro clima planning documentation and application recommendations. If you have any questions, please call the pro clima technical hotline Ireland and UK:  
Phone: +353 46 9432104  
Fax: +353 46 9432435  
[info@ecologicalbuildingsystems.com](mailto:info@ecologicalbuildingsystems.com)

#### For Stockists contact

##### Ireland

Phone: +353 (0)46 9432104

Fax: +353 (0)46 9432435

##### UK

Phone: +44 (0)1228 711 511

Fax: +44 (0)1228 712 280

#### Ecological Building Systems

[info@ecologicalbuildingsystems.com](mailto:info@ecologicalbuildingsystems.com)

[www.ecologicalbuildingsystems.com](http://www.ecologicalbuildingsystems.com)

#### MOLL bauökologische Produkte GmbH

Rheintalstraße 35 - 43

68723 Schwetzingen

Germany

[www.proclima.com](http://www.proclima.com)

---

For over 20 years, Ecological Building Systems has been at the forefront of environmental and sustainable building products supplying a range of innovative airtightness solutions and natural insulations backed up with expert technical support.

**As product suppliers in the UK and Ireland, we're happy to assist you with your projects and have expert technical and sales advice on hand.**



**Call us**

**Great Britain** +44 (0)1228 711511

**Ireland** +353 46 9432104



**Email us**

[info@ecologicalbuildingsystems.com](mailto:info@ecologicalbuildingsystems.com)



**Find us**

**Great Britain** Ecological Building Systems UK Ltd.,  
Cardewlees, Carlisle, Cumbria, CA5 6LF,  
United Kingdom

**Ireland** Ecological Building Systems Ltd.,  
Main Street, Athboy. Co. Meath, C15 Y678,  
Republic of Ireland