

## SuperPan® Tech Vapourstop EZ

### TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			10-13	>13-20	>20-25	>25-32	>32-40
Density (*)	EN 323:1993	kg/m <sup>3</sup>	715/710	700/690	690/680	670	650
Thickness Swelling 24h	EN 317:1993	%	10	10	10	10	9
Bending Strength	EN 310:1993	N/mm <sup>2</sup>	28	28	26	20	19
Modulus of Elasticity	EN 310:1993	N/mm <sup>2</sup>	3500	3500	3200	3000	2800
Swelling In Thickness after Cyclic Test (V313)	EN 321:2001 / EN 317:1993	%	12	12	11	10	9
Internal Bond after Cyclic Test (V313)	EN 321:2001 / EN 319:1993	N/mm <sup>2</sup>	0,25	0,22	0,20	0,17	0,15
Surface Soundness	EN 311:2002	N/mm <sup>2</sup>	>1,1	>1,1	>1,1	>1,1	>1,1
Formaldehyde emission	EN 717-1:2004	ppm	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05
Reaction to fire	EN 13501-1:2018	Euroclass	CWFT	CWFT	CWFT	CWFT	CWFT
Dimensional Movement Length/Width	EN 318:2002	%	0,4	0,4	0,4	0,4	0,4
Dimensional Movement Thickness	EN 318:2002	%	6	6	6	6	6
Screw Holding. Edge	EN 320:2011	N	800	800	800	800	800
Screw Holding. Surface	EN 320:2011	N	1100	1100	1100	1100	1100
Water vapour permeability Wet cup	EN13986:2004+A1:2015	μ	240	240	240	240	240
Water vapour permeability Dry cup	EN13986:2004+A1:2015	μ	1150	1150	1150	1150	1150
Moisture Content	EN 322:1993	%	8+/-3	8+/-3	8+/-3	8+/-3	8+/-3
Internal Bond	EN 319:1993	N/mm <sup>2</sup>	0,60	0,60	0,55	0,50	0,45

### TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			10-13	>13-20	>20-25	>25-32	>32-40
Thicknesses	EN 324-1:1993	mm	+/-0,30	+/-0,30	+/-0,30	+/-0,30	+/-0,30
Lenght & Width	EN 324-1:1993	mm	+/-5	+/-5	+/-5	+/-5	+/-5
Squareness	EN 324-2:1993	mm/m	+/-2	+/-2	+/-2	+/-2	+/-2
Edge Straightness	EN 324-2:1993	mm/m	+/-1,5	+/-1,5	+/-1,5	+/-1,5	+/-1,5

(\*) Values to be considered as a rough guide only.

These physical-mechanical values comply with the values established in European standard EN 312:2010, Tables 7 and 8. - Structural boards for use in humid conditions (Type P5).

CWFT: Reaction to fire classification without the need of testing, according to European Commission Decision 2007/348/EC.

Product with very low formaldehyde emission ≤ 0,05 ppm (≤ 0,062 mg/m<sup>3</sup>) measured under European Standard EN 717-1:2004 that complies with the specifications of Class E1 defined in th EN 312:2010 European Standard.

Product compliant with US EPA TSCA Title VI and California Code of Regulation 17 ATCM 93120, Phase 2.

Reports and certificates relating to this product are available upon request.

Handling/Storage Recommendations:

Bords should always be stored under cover and on a flat surface.  
Optimal storage conditions are 65% humidity; avoid environments that are either too dry or too damp.  
Under no circumstances should there be direct contact with water.  
Spacers must always be vertically aligned.  
Under no circumstances should boards be stacked more than 4 high.

If the packaging is damaged during handling, it must be re-packaged to ensure the product's proper preservation.

Failure to observe the stated stacking conditions, as well as changes in humidity or temperature in warehouses or processing areas, can lead to



## SuperPan® Tech Vapourstop EZ

irreversible distortion and warping.

Wood used by Finsa in the production of fibreboards (MDF) is a mixture primarily of pine and eucalyptus. Particleboard production also uses a mixture primarily of pine and eucalyptus, with the addition of recycled wood from diverse species. All wood is obtained in accordance with PEFC and FSC chain of custody requirements, and in compliance with EUTR/EUDR regulations.

It is the duty and responsibility of the end user to evaluate, in accordance with relevant local health and safety regulations, all risks presented to any persons involved in processing/transforming/handling the materials. A detailed plan of procedure and necessary checks must be in place to ensure preventive measures are appropriately enforced to minimise all risk; eg. manual handling, dust extraction if cutting/sanding/machining, use of PPE, etc.

For over 20 years, Ecological Building Systems has been at the forefront of environmental and sustainable building products supplying a range of innovative airtightness solutions and natural insulations backed up with expert technical support.

**As product suppliers in the UK and Ireland, we're happy to assist you with your projects and have expert technical and sales advice on hand.**



**Call us**

**Great Britain** +44 (0)1228 711511

**Ireland** +353 46 9432104



**Email us**

[info@ecologicalbuildingsystems.com](mailto:info@ecologicalbuildingsystems.com)



**Find us**

**Great Britain** Ecological Building Systems UK Ltd.,  
Cardewlees, Carlisle, Cumbria, CA5 6LF,  
United Kingdom

**Ireland** Ecological Building Systems Ltd.,  
Main Street, Athboy. Co. Meath, C15 Y678,  
Republic of Ireland