



SUPERPAN VAPOURSTOP

TECHNICAL DATA-AVERAGE VALUES

Rev: 01/18/2021

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			>10/13	>13/20	>20/25	>25/32	>32/40
DENSITY (*)	EN 323	kg/m3	750	720	710	700	675
INTERNAL BOND	EN 319	N/mm2	0,60	0,60	0,55	0,50	0,45
BENDING STRENGTH	EN 310	N/mm2	28	28	26	20	19
MODULUS OF ELASTICITY	EN 310	N/mm2	3500	3500	3200	3000	2800
THICKNESS SWELLING 24 H	EN 317	%	10	10	10	10	9
DIMENSIONAL MOVEMENT LENGTH/WIDTH	EN 318	%	0,4	0,4	0,4	0,4	0,4
DIMENSIONAL MOVEMENT TICKNESS	EN 318	%	6	6	6	6	6
SURFACE SOUNDNESS	EN 311	N/mm2	>1,1	>1,1	>1,1	>1,1	>1,1
MOISTURE CONTENT	EN 322	%	8+/-3	8+/-3	8+/-3	8+/-3	8+/-3
FORMALDEHYDE EMISSION	EN 717-1	ppm	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05
SCREW HOLDING. EDGE	EN 320	N	800	800	800	800	800
SCREW HOLDING. SURFACE	EN 320	N	1100	1100	1100	1100	1100
REACTION TO FIRE TABLA 8 EN EN 13986:2006+A1:2015	EN 13501-1	Class	D-s2,d0**	D-s2,d0***	D-s2,d0	D-s2,d0	D-s2,d0
REACTION TO FIRE TABLA 8 EN EN 13986:2004+A1:2015 I	EN 13501-1	Class	Dfl-s1	Dfl-s1	Dfl-s1	Dfl-s1	Dfl-s1
SWELLING IN THICKNESS AFTER CYCLIC TEST (V313)	EN 321 / EN 317	%	12	12	11	10	9
INTERNAL BOND AFTER CYCLIC TEST (V313)	EN 321 / EN 319	N/mm2	0,25	0,22	0,20	0,17	0,15
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0,10	0,10	0,10	0,10	0,10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0,25	0,25	0,25	0,25	0,25
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/(m·K)	0,15	0,14	0,14	0,14	0,14
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	26	28	30	31	32
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	1150	1150	1150	1150	1150
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	240	240	240	240	240
BIOLOGICAL DURABILITY USE	EN 335	Class of use	1 & 2	1 & 2	1 & 2	1 & 2	1 & 2
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	ppm	<5	<5	<5	<5	<5
MECHANICAL DURABILITY	EN 13986:2004+A1:2015	Kmod Kdef	Tabla 3.1, EN 1995-1:2004; 3.2, EN 1995-1:2004;	Tabla 3.1, EN 1995-1:2004; 3.2, EN 1995-1:2004;	Tabla 3.1, EN 1995-1:2004; 3.2, EN 1995-1:2004;	Tabla 3.1, EN 1995-1:2004; 3.2, EN 1995-1:2004;	Tabla 3.1, EN 1995-1:2004; 3.2, EN 1995-1:2004;

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			>10/13	>13/20	>20/25	>25/32	>32/40
THICKNESS	EN 324-1	mm	+/-0,30	+/-0,30	+/-0,30	+/-0,30	+/-0,30

LENGTH/WIDTH	EN-324-1	mm	+/-5	+/-5	+/-5	+/-5	+/-5	
SQUARENESS	EN 324-2	mm/m	+/-2	+/-2	+/-2	+/-2	+/-2	
EDGE STRAIGHTNESS	EN-324-2	mm/m	+/-1,5	+/-1,5	+/-1,5	+/-1,5	+/-1,5	
COLOR RESISTANCE TO UV LIGHT (XENON LAMP)			EN 14323; EN 14323			Blue wool scale, n°		>6

(*) VALUES TO BE CONSIDERED AS A ROUGH GUIDE ONLY.

(**) Mounted without an air gap behind the superPan VapourStop. Mounted with a closed air gap not bigger than 22 mm behind the superPan VapourStop classification D-s2,d2. Classification E for any other more restrictive condition. Commission Decision 2007/348/EC

(***) Mounted without an air gap behind the superPan VapourStop, or with a closed air gap behind the superPan VapourStop for thicknesses equal or greater than 15mm or with an open air gap behind the wuperPan VapourStop for thicknesses equal or greater than 18 mm . Mounted with a closed air gap not bigger than 22mm behind the superPan VapourStop classification D-s2,d2 in thicknesses between 10 and 18 mm. Commission Decision 2007/348/EC.

The properties of permeability of water vapor for wet and dry glass cup Superpan VapourStop board, have been tested according to DIN EN ISO 12572 laboratory Materialprüfanstalt MPA Eberswalde Brandenburg GmbH ; in (Test Report No. 31/13 /1987/ 02 / μ)

These physical-mechanical values improve/comply with the P5 classification established in EN 312:2010 European Standard, Tables 7 and 8. Structural boards used in moist environments (Type P5). Requirements for the specified mechanical and swelling properties. Requirements for use in humid contitions.

SuperPan VapourStopis a low formaldehyde emission product E05 (≤ 0.05 ppm EN 717-1) and meets Class E1 requirements as defined in EN 14322 European Standard.

SuperPan VapourStop holds CE Certificate of conformity of the factory production control issued by the European Notified Body AENOR. (SELECT)