SOLITEX ADHERO® VISTO

Transparent full-surface adhesive airtightness and weathering-protection membrane



Technical data

	Material
Functional film	Polyethylene copolymer
Protective film	Polypropylene
Adhesive	Water-resistant SOLID adhesive
Release film	Silicone-coated PE film

Colour Translucent Surface weight BS EN 1849-2 210 g/m² Thickness BS EN 1849-2 0.35 mm Water vapour resistance factor μ BS EN 1931 8 570 sd value BS EN 1931 3 m g value ASTM E96 Procedure B 15 MN·s/g Fire class BS EN 13501-1 C-s1, d0 Outdoor exposure Cen./Nth. Europe & Canada/Nth. US: 3 months; RoW: 6 weeks Driving rain test ZVDH / TU Berlin Passed Hail impact resistance BS EN 13583 Passed Hail impact resistance, floors/ walls VKF / AEAI Class HR 5 Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) 2024 UDB Suitable as temporary roof covering (Germany) 2VDH Yes Water column BS EN ISO 811 10 000 mm Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 60% / 60% Nail tear resistance MD/CD BS EN 1297 / B	Property	Regulation	Value
Thickness BS EN 1849-2 0.35 mm Water vapour resistance factor μ BS EN 1931 8 570 sd value BS EN 1931 3 m g value ASTM E96 Procedure B 15 MN·s/g Fire class BS EN 13501-1 C-s1, d0 Outdoor exposure Cen./Nth. Europe & Canada/Nth. US: 3 months; RoW: 6 weeks Driving rain test ZVDH / TU Berlin Passed Hail resistance BS EN 13583 Passed Hail impact resistance, floors/ VKF / AEAI Class HR 5 Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) ZVDH-Produktdatenblatt (Germany) Tyes Water column BS EN ISO 811 10 000 mm Water column BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 190 N/5 cm / 180 N/5 cm BS EN 13859-1 (A) / -2 (A) 60% / 60%	Colour		Translucent
Water vapour resistance factor µ BS EN 1931 8 570 sd value BS EN 1931 3 m g value ASTM E96 Procedure B 15 MN·s/g Fire class BS EN 13501-1 C-s1, d0 Outdoor exposure Cen,/Nth. Europe & Canada/Nth. US: 3 months; RoW: 6 weeks Driving rain test ZVDH / TU Berlin Passed Hail resistance BS EN 13583 Passed Hail impact resistance, floors/ walls Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) ZVDH-Produktdatenblatt 2024 Suitable as temporary roof covering (Germany) Water column BS EN ISO 811 10 000 mm Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) Passed Passed Passed Flexibility after artificial ageing BS EN 1297 / BS EN 1296 (EN 1297 / BS EN 1296 (EN 1297 (EN 1296 (EN 1297 (EN 1296 (EN 1297 (EN 1296 (EN 1297 (EN 1297 (EN 1297 (EN 1296 (EN 1297 (EN 129	Surface weight	BS EN 1849-2	210 g/m²
sd value B5 EN 1931 3 m g value ASTM E96 Procedure B 15 MN-s/g Fire class B5 EN 13501-1 C-s1, d0 Outdoor exposure Cen./Nth. Europe & Canada/Nth. US: 3 months; RoW: 6 weeks Driving rain test ZVDH / TU Berlin Passed Hail resistance BS EN 13583 Passed Hail impact resistance, floors/ walls VKF / AEAI Class HR 5 Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) ZVDH-Produktdatenblatt 2024 UDB Suitable as temporary roof covering (Germany) ZVDH Yes Water column BS EN ISO 811 10 000 mm Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 190 N/5 cm / 180 N/5 cm Elongation MD/CD BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing BS EN 1297 / BS EN 1296, EN 1296, EN 1296, EN 1296, EN 1296 Permanent -40 °C to 80 °C Temperature resistance EN 1109, EN 1296, EN 1296, EN 1296 Permanent -40 °C to 80 °C <td>Thickness</td> <td>BS EN 1849-2</td> <td>0.35 mm</td>	Thickness	BS EN 1849-2	0.35 mm
g value ASTM E96 Procedure B 15 MN-s/g Fire class BS EN 13501-1 C-s1, d0 Outdoor exposure Cen./Nth. Europe & Canada/Nth. US: 3 months; RoW: 6 weeks Driving rain test ZVDH / TU Berlin Passed Hail resistance BS EN 13583 Passed Hail impact resistance, floors/ walls Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) ZVDH-Produktdatenblatt 2024 Suitable as temporary roof covering (Germany) ZVDH Yes Water column BS EN ISO 811 10 000 mm Watertightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 190 N/5 cm / 180 N/5 cm Elongation MD/CD BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1297 Thermal conductivity 0.04 W/(m-K)	Water vapour resistance factor μ	BS EN 1931	8 570
Fire class BS EN 13501-1 C-s1, d0 Outdoor exposure Driving rain test Driving rain test EN 13583 Driving rain test EN 13583 Passed Hail resistance BS EN 13583 Passed Hail impact resistance, floors/ walls Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) Suitable as temporary roof covering (Germany) Water column BS EN 150 811 D000 mm Watertightness, non-aged/aged* EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) BS EN 12310-1 Elongation MD/CD BS EN 12310-1 BS EN 1296 Flexibility after artificial ageing BS EN 11996, EN 1296 Flexibility at low temperature EN 1109, EN 1296, EN 1297 Permanent -40 °C to 80 °C Temperature resistance C-s1, d0 Cen./Nth. Europe &t Canada/Nth. US: 3 months; RoW: 6 weeks Passed Class HR 5 UDB UDB V*F / AEAI Class HR 5 UDB Valy UDB Ves Ves W1 / V 1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) Flexibility after artificial ageing BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 Permanent -40 °C to 80 °C CO.04 W/(m·K)	sd value	BS EN 1931	3 m
Outdoor exposure Cen./Nth. Europe & Canada/Nth. US: 3 months; RoW: 6 weeks Driving rain test ZVDH / TU Berlin Passed Hail resistance BS EN 13583 Passed Hail impact resistance, floors/ walls Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) ZVDH-Produktdatenblatt 2024 Suitable as temporary roof covering (Germany) Water column BS EN ISO 811 Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing BS EN 1109 Flexibility at low temperature BS EN 1109, EN 1296, EN 1297 Permanent -40 °C to 80 °C Temperature resistance Canada/Nth. US: 3 months; RoW: 6 weeks Passed Passed Passed Passed Permanent -40 °C to 80 °C C.04 W/(m·K)	g value	ASTM E96 Procedure B	15 MN·s/g
Driving rain test	Fire class	BS EN 13501-1	C-s1, d0
Hail resistance BS EN 13583 Passed Hail impact resistance, floors/walls VKF / AEAI Class HR 5 Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) 2VDH-Produktdatenblatt 2024 Suitable as temporary roof covering (Germany) 2VDH Yes Water column BS EN ISO 811 10 000 mm Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 190 N/5 cm / 180 N/5 cm Elongation MD/CD BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing Plexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1297 / BS EN 1296, EN 1297 Permanent -40 °C to 80 °C Thermal conductivity 0.04 W/(m·K)	Outdoor exposure		
Hail impact resistance, floors/walls Slip resitance DGUV Test R10 / V - Roofing underlay membrane (Germany) Suitable as temporary roof covering (Germany) Water column BS EN ISO 811 Airtightness Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) RS EN 12310-1 BS EN 1250 N / 250 N *) Durability after artificial ageing Flexibility at low temperature BS EN 1109, EN 1296, EN 1297 Permanent -40 °C to 80 °C Thermal conductivity Class HR 5 R10 / V - R10 / V	Driving rain test	ZVDH / TU Berlin	Passed
Walls Slip resitance DGUV Test Roofing underlay membrane (Germany) ZVDH-Produktdatenblatt 2024 UDB Suitable as temporary roof covering (Germany) Water column BS EN ISO 811 Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1109, EN 1296, EN 1297 Permanent -40 °C to 80 °C Thermal conductivity O.04 W/(m·K)	Hail resistance	BS EN 13583	Passed
Roofing underlay membrane (Germany) Suitable as temporary roof covering (Germany) Water column Water tightness, non-aged/aged* Airtightness Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (B) Elongation MD/CD BS EN 13859-1 (A) / -2 (B) Elongation MD/CD BS EN 13859-1 (A) / -2 (B) Elongation MD/CD BS EN 12310-1 BS EN 12310-1 BS EN 1250 N *) Durability after artificial ageing BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 Flexibility at low temperature EN 1109, EN 1296, EN 1297 Temperature resistance EN 1109, EN 1296, EN 1297 Thermal conductivity O.04 W/(m·K)		VKF / AEAI	Class HR 5
Germany) Suitable as temporary roof covering (Germany) Water column BS EN ISO 811 10 000 mm Watertightness, non-aged/aged* Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 Flexibility at low temperature BS EN 1109, EN 1296, EN Permanent -40 °C to 80 °C Thermal conductivity O.04 W/(m·K)	Slip resitance	DGUV Test	R10 / V -
Covering (Germany) Water column BS EN ISO 811 10 000 mm Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 12310-1 BS EN 12310-1 BS EN 1297 / BS EN 1296 Flexibility after artificial ageing BS EN 1109 Flexibility at low temperature BS EN 1109 Flexibility at low temperature EN 1109, EN 1296, EN Permanent -40 °C to 80 °C Thermal conductivity O.04 W/(m·K)	· .		UDB
Watertightness, non-aged/aged* BS EN 1928 W1 / W1 Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 190 N/5 cm / 180 N/5 cm Elongation MD/CD BS EN 13859-1 (A) / -2 (A) 60% / 60% Nail tear resistance MD/CD BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing Passed Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1109, EN 1296, EN 1297 / BS EN Permanent -40 °C to 80 °C Thermal conductivity O.04 W/(m·K)		ZVDH	Yes
Airtightness Passed Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) 190 N/5 cm / 180 N/5 cm Elongation MD/CD BS EN 13859-1 (A) / -2 60% / 60% Nail tear resistance MD/CD BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing 1296 Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1109, EN 1296, EN 1297 Thermal conductivity Passed Passed Passed Passed Passed Passed Passed Passed Pormanent -40 °C Temperature resistance O.04 W/(m·K)	Water column	BS EN ISO 811	10 000 mm
Tensile strength MD/CD BS EN 13859-1 (A) / -2 (A) Elongation MD/CD BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) BS EN 13859-1 (A) / -2 (A) 60% / 60% Nail tear resistance MD/CD BS EN 12310-1 250 N / 250 N *) Durability after artificial ageing BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 Flexibility at low temperature BS EN 1296, EN Permanent -40 °C to 80 °C Thermal conductivity 0.04 W/(m·K)	Watertightness, non-aged/aged*	BS EN 1928	W1 / W1
Elongation MD/CD (A) BS EN 13859-1 (A) / -2 (A) Rail tear resistance MD/CD BS EN 12310-1 *) Durability after artificial ageing Place BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 Flexibility at low temperature BS EN 1109 Flexibility at low temperature EN 1109, EN 1296, EN 1297 Thermal conductivity 1296 Thermal conductivity 1200 N/5 cm / 180 N/5 cm 60% / 60% Passed Passed Passed Permanent -40 °C O.04 W/(m·K)	Airtightness		Passed
Nail tear resistance MD/CD (A) BS EN 12310-1 *) Durability after artificial ageing Passed Flexibility at low temperature BS EN 1297 / BS EN 1296 Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1109, EN 1296, EN Permanent -40 °C to 80 °C Thermal conductivity 0.04 W/(m·K)	Tensile strength MD/CD	` ' '	190 N/5 cm / 180 N/5 cm
*) Durability after artificial ageing BS EN 1297 / BS EN 1296 Passed Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1109, EN 1296, EN 1297 Permanent -40 °C to 80 °C Thermal conductivity 0.04 W/(m·K)	Elongation MD/CD	` ' '	60% / 60%
Flexibility at low temperature BS EN 1109 -40 °C Temperature resistance EN 1109, EN 1296, EN 1297 Permanent -40 °C to 80 °C Thermal conductivity 0.04 W/(m·K)	Nail tear resistance MD/CD	BS EN 12310-1	250 N / 250 N
Temperature resistance EN 1109, EN 1296, EN Permanent -40 °C to 80 °C Thermal conductivity 0.04 W/(m·K)	*) Durability after artificial ageing		Passed
Thermal conductivity 1297 Thermal conductivity 0.04 W/(m·K)	Flexibility at low temperature	BS EN 1109	-40 °C
	Temperature resistance		Permanent -40 °C to 80 °C
CE labelling BS EN 13859-1/-2 Yes	Thermal conductivity		0.04 W/(m·K)
	CE labelling	BS EN 13859-1/-2	Yes

Areas of application

Temporary protection for floors during construction

Thanks to its full-surface adhesion, this membrane provides temporary weathering-protection for intermediate floors on multi-storey CLT (cross-laminated timber) or wooden-frame buildings during the construction period.



Supply form

Art. no.	Length	Width	Splits on release film	Contents	Weight	Sales unit	Container	GTIN
1AR04302	30 m	0.3 m	No split	9 m²	2.5 kg	1	170	4026639243027
1AR04051	30 m	0.5 m	No split	15 m²	3.5 kg	1	72	4026639240514
1AR04036	30 m	1 m	0.25 0.75 m	30 m²	7 kg	1	48	4026639240361
1AR04026	30 m	1.5 m	0.25 1.25 m	45 m²	10.5 kg	1	24	4026639240262

Advantages

- ✓ Protects the underlying structure against weathering during the construction phase
- 🗸 3 months of outdoor exposure in Central/Northern Europe, Canada and the northern United States; 6 weeks in the rest of the world
- ✓ Highly transparent: all markings, connectors and notches/recesses on timber floors remain visible
- ✓ Excellent occupational safety, even in wet conditions: anti-slip behaviour certified by German Social Accident Insurance (DGUV)
- ✓ Water-resistant SOLID adhesive ensures reliable adhesion to the subsurface and within overlap areas
- ✓ Acts as a stable separating layer for additional floor structures / timber-concrete composite (TCC) floors
- ✓ Improved noise insulation and protection against toxic gases during fires thanks to airtight floor/ceiling structures.

Substrates

Clean subsurfaces before applying the membranes – remove any protruding elements. Adhesion is not possible on frozen surfaces. There must be no water-repellent substances (e.g., grease or silicone) on surfaces where adhesives are to be applied. Subsurfaces must be sufficiently dry and stable.

It is your responsibility to check the suitability of the subsurface; adhesion tests may be necessary in certain cases.

General conditions

Temporary protection for floors during construction

SOLITEX ADHERO VISTO is to be installed with the printed side facing the installation technician; it can be installed on stable board substrates (e.g. CLT, OSB, chipboard and plywood sheets). Recesses in the substrate – such as slots, grooves etc. – can lead to increased seepage underneath SOLITEX ADHERO membranes and should be avoided, if possible. To achieve waterproof installation, membranes must be installed with no folds or creases. When installing the membranes, rub them firmly to secure the adhesive bond using a sweeping brush or the PRESSFIX XL tool, for example.

If SOLITEX ADHERO VISTO is to be applied to floor elements during the pre-fabrication stage, TESCON VANA can be used to tape the element/membrane joints on the construction site. There should be a width of at least 5 cm of tape on each element. Alternatively, the SOLITEX ADHERO VISTO strip that is available in a width of 0.30 m can be used to cover these joints.

These strips should also be used if the elements are connected with butt boards. The width of the adhesive bond zone must be at least 10 cm on both elements. SOLITEX ADHERO VISTO strips are not suitable for other substrates. Other connections should be taped with TESCON VANA, ensuring that a width of at least 5 cm is covered on the SOLITEX ADHERO VISTO membrane. Continue the sealed transition to a height of approx. 10-15 cm at adjacent vertical elements.

SOLITEX ADHERO VISTO can provide temporary weathering-protection for intermediate floors on multi-storey CLT (cross-laminated timber) or wooden-frame buildings during construction for a period of up to 3 months in Great Britain and Ireland, the rest of Northern and Central Europe, Canada and the northern United States (ASHRAE Climate Zones 4-8), and up to 6 weeks in Southern Europe, the rest of the United States (ASHRAE Climate Zones 1-3) and the rest of the world

Water must be drained from the surface of the building structure, e.g. using ADHERO Floor Drain. A short-term build-up depth (max. 24 hours) of 30 mm should not be exceeded.

Bitumen membranes can be welded onto this membrane; the applicable regulations are to be observed.



Data sheet SOLITEX ADHERO VISTO









*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes missions)

Tested for hazardous substances according to







The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about application and construction is given in the proclima planning documentation and application recommendations. If you have any questions, please call the pro-clima technical hotline Ireland and UK:

Phone: +353 46 9432104 Fax: +353 46 9432435 info@ecologicalbuildingsystems.com

For Stockists contact

Ireland

Phone: +353 (0)46 9432104 Fax: +353 (0)46 9432435

UK

Phone: +44 (0)1228 711 511 Fax: +44 (0)1228 712 280

Ecological Building Systems

info@ecologicalbuildingsystems.com www.ecologicalbuildingsystems.com

MOLL bauökologische Produkte GmbH

Rheintalstraße 35 - 43 68723 Schwetzingen Germany www.proclima.com



For over 20 years, Ecological Building Systems has been at the forefront of environmental and sustainable building products supplying a range of innovative airtightness solutions and natural insulations backed up with expert technical support.

As product suppliers in the UK and Ireland, we're happy to assist you with your projects and have expert technical and sales advice on hand.



Call us

Great Britain +44 (0)1228 711511 Ireland +353 46 9432104



Email us

info@ecologicalbuildingsystems.com



Find us

Great Britain Ecological Building Systems UK Ltd., Cardewlees, Carlisle, Cumbria, CA5 6LF, United Kingdom

Ireland Ecological Building Systems Ltd., Main Street, Athboy. Co. Meath, C15 Y678, Republic of Ireland

